

Polystrand™ IE 6537

Continuous glass-reinforced thermoplastic polypropylene composite

Key Characteristics

Product description

Polystrand™ IE 6537 is a polypropylene-based thermoplastic unidirectional tape, which balances strength and toughness with light weight. Applications include structural components for transportation, and as reinforcement for molded or thermoformed components. The use of PP resin imparts good chemical and solvent resistance. Unidirectional tapes are available in rolls 25" wide. Custom slit widths and finished stampings are also available. Multi-ply laminates are available with plies arranged in 0 or 90 degree orientations, with maximum roll width of 125".

Technical Properties of Unidirectional Tape

Typical Properties

PROPERTY	TEST METHOD	UNITS	DATA
Glass Content	ASTM D3647	wt%	65
Areal weight	--	oz/yd2 (g/m2)	14.8 (499)
Thickness	--	In (mm)	0.015 (0.38)
Flexural modulus	ASTM D790	MPsi (MPa)	3.92 (27)
Flexural Strength	ASTM D790	Ksi (MPa)	62 (427)
Longitudinal Tensile Modulus	ASTM D3039	MPsi (GPa)	4.14 (28.5)
Longitudinal Tensile Strength	ASTM D3039	Ksi (MPa)	50.3 (347)
In-Plane Poisson's Ratio	ASTM D3039	--	0.27
Transverse Tensile Modulus	ASTM D3039	MPsi (GPa)	0.28 (1.9)
Transverse Tensile Strength	ASTM D3039	Ksi (MPa)	1.3 (9.0)
Longitudinal Compressive Modulus	ASTM D6641	MPsi (GPa)	0.52 (3.6)
Longitudinal Compressive Strength	ASTM D6641	Ksi (MPa)	17.3 (119)
Transverse Compressive Modulus	ASTM D6641	MPsi (GPa)	0.10 (0.66)
Transverse Compressive Strength	ASTM D6641	Ksi (MPa)	3.1 (21)
In-Plane Shear Modulus	ASTM D7078	MPsi (GPa)	0.13 (0.87)
In-Plane Shear Strength	ASTM D7078	ksi (GPa)	1.6 (11.2)
Transverse Shear Modulus	ASTM D7078	MPsi (GPa)	0.13 (0.9)
Transverse Shear Strength	ASTM D7078	ksi (GPa)	4.2 (28.8)

Notes

NOTE: The data listed herein reflect typical sheet properties. They are the latest available at the time of publication and are reliable to the best knowledge of PolyOne. The properties are listed solely to give general guidance and are not to be construed as a warranty or representation for of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. We sell the products without

warranty. Buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

Processing

Polystrand™ IE 6537 process temperature is 390-420F (199-216C). Contact PolyOne for detailed set-up and processing guidelines.

Please contact PolyOne for data relating to a specific application or equipment.

Availability

Polystrand™ IE 6537 roll or laminated sheet is available in the US, EU and Asia Pacific regions.

CONTACT INFORMATION

For additional information, please contact PolyOne Advanced Composites at +1.866.POLYONE (+1.866.765.9663) or visit our web site at www.polyone.com.

Copyright © 2017, PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.